

## **AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

## **LISTING OF CLAIMS:**

Claim 1 to 10. (Canceled).

11. (Currently Amended) A perforated nonwoven fabric, comprising:  
interlaced continuous microfiber filaments having a titer in a range of 0.05 to 0.40 dtex, the microfiber filaments being composed of at least two thermoplastic polymers having different hydrophobicity and having one of a pie filament cross-section and a hollow pie filament cross-section, from which split filaments have been released, perforations being clearly formed and being free of split-fiber filaments;

wherein the perforated nonwoven fabric has a mass per unit area of 8 to 17 g/m<sup>2</sup>; and  
wherein the perforated nonwoven fabric is impregnated with ~~0 to 0.60% by weight in relation to a nonwoven weight of~~ at least one surface-active agent, and  
wherein the perforated nonwoven fabric does not exceed 0.60% by weight in relation to the nonwoven weight of the at least one surface-active agent.

12. (Previously Presented) The perforated nonwoven fabric according to claim 11, wherein the perforations are evenly spaced and have an individual-hole area of 0.01 to 0.60 cm<sup>2</sup>.

13. (Previously Presented) The perforated nonwoven fabric according to claim 11, wherein a ratio between a maximum distance from points on a nonwoven surface to a next perforation and a minimum distance is 1:1 to 2:1.

14. (Previously Presented) The perforated nonwoven fabric according to claim 11, wherein an open hole area is 8 to 40%.

15. (Previously Presented) The perforated nonwoven fabric according to claim 11, wherein the microfiber filaments include polyolefin and polyester filaments in a weight ratio in a range of 20:80 to 80:20.

16. (Canceled).

17. (Previously Presented) The perforated nonwoven fabric according to claim 11, wherein a strike through value of after one minute is less than three seconds, a rewet value is less than 0.59 and a tensile strength in a longitudinal direction is at least 30N/5 cm.

18. (Currently Amended) A method for producing a perforated nonwoven fabric, comprising the steps of:

laying up one of splittable pie and splittable hollow pie continuous fibers, a cross-section of which having at least two different thermoplastic polymers having different hydrophobicity in an alternating cake-piece arrangement to form a nonwoven fabric;

after the laying up step, splitting and entangling the split filaments by high-pressure water jets to form interlaced microfiber filaments;

after the splitting and entangling step, perforating the nonwoven fabric using high-pressure water jets; and

impregnating the perforated nonwoven fabric with ~~0 to 0.60% by weight in relation to a nonwoven weight of~~ at least one surface-active agent, wherein the perforated nonwoven fabric does not exceed 0.60% by weight in relation to the nonwoven weight of the at least one surface-active agent.

19. (Previously Presented) The method according to claim 18, wherein the perforating step is performed on hydroextraction and hole-forming cylinders having elevations on a surface thereof.

20. (Currently Amended) A hygiene product, comprising:

a topsheet having a perforated nonwoven fabric including interlaced continuous microfiber filaments having a titer in a range of 0.05 to 0.40 dtex, the microfiber filaments being composed of at least two thermoplastic polymers having different hydrophobicity and having one of a pie filament cross-section and a hollow pie filament cross-section, from which split filaments have been released, perforations being clearly formed and being free of split-fiber filaments;

wherein the perforated nonwoven fabric has a mass per unit area of 8 to 17 g/m<sup>2</sup>; and

wherein the perforated nonwoven fabric is impregnated with ~~0 to 0.60% by weight in relation to a nonwoven weight of~~ at least one surface-active agent, and

wherein the perforated nonwoven fabric does not exceed 0.60% by weight in relation to the nonwoven weight of the at least one surface-active agent.

21. (Previously Presented) The hygiene product according to claim 20, wherein the hygiene product includes at least one of a diaper and a sanitary napkin.

22. (Previously Presented) The hygiene product according to claim 20, wherein the perforations are evenly spaced and have an individual-hole area of 0.01 to 0.60 cm<sup>2</sup>.

23. (Previously Presented) The hygiene product according to claim 20, wherein a ratio between a maximum distance from points on a nonwoven surface to a next perforation and a minimum distance is 1:1 to 2:1.

24. (Previously Presented) The hygiene product according to claim 20, wherein an open hole area is 8 to 40%.

25. (Previously Presented) The hygiene product according to claim 20, wherein the microfiber filaments include polyolefin and polyester filaments in a weight ratio in a range of 20:80 to 80:20.

26. (Canceled).

27. (Previously Presented) The hygiene product according to claim 20, wherein a strike through value after one minute is less than three seconds, a rewet value is less than 0.59 and a tensile strength in a longitudinal direction is at least 30N/5 cm..

28. (Previously Presented) The perforated nonwoven fabric of claim 11, wherein the at least one surface-active agent is a wetting agent one of (a) in dispersed form and (b) dissolved in water.

29. (Previously Presented) The method of claim 18, wherein the at least one surface-active agent is a wetting agent one of (a) in dispersed form and (b) dissolved in water.

30. (Previously Presented) The hygiene product of claim 20, wherein the at least one surface-active agent is a wetting agent one of (a) in dispersed form and (b) dissolved in water.